

## Letter of Certification

P.O. Box 43167 Atlanta, GA 30336 800-299-5305

## .019 X 24" X 50' – Aluminum Trim Coil Polyester Trim Coil 280 WHITE

## Spectra Metal Sales, Inc. is a member of the National Coil Coating Association and uses the NCCA's standards as guidelines for physical testing.

- The Aluminum used is alloy 3105-H28 or 3105-H25 which meets the specifications set forth in the "Aluminum Standards and Data 2006" published by the Aluminum Association. The finished gauge of the Aluminum for this coil is .019, +/- .002.
- The surface of the Aluminum sheet is thoroughly cleaned and dried to remove impurities and coated with Bonderite 1402-W non-cyanide chromate conversion coating.
- The Aluminum's inside and outside coating is a thermo polyester paint which is roll coated and baked per manufactures specifications.
- The DFT range of the applied topcoat finish is .60 mils, +/- .2 mils.

## Spectra Metal Sales, Inc. has a complete line of state of the art quality control equipment which includes:

Hunter DP-9000 Colormeter
Garner Impact Tester
Garner Cross Hatch Tester
Fischer Dual Scope Film Thickness Gauge
Gardner Gloss Meter

• The paint specifications used for our smooth white polyester coated trim coil are as follows:

Gloss (60°): 10 +/- 2 Units (varies by color) Solvent Resistance: 100 Double rubs (M.E.K.)

Flexibility: .019 (+/-.002) 2 T Bend minimum

Impact (N.T.O.): 1-1/2 Times metal thickness in Inch-Lbs (ASTM D 2794)

Pencil Hardness: F - 2H

Humidity Resistance: No blistering, loss of adhesion after 1,000 hours exposure to 100%

relative humidity. (ASTM D 2247)

Salt Spray Resistance: No field blistering and no more than 1/16" creep from a score line

after neutral salt spray testing for 1,000 Hours (ASTM B 117)

Weathering Resistance: Will withstand ten years outdoor southern exposure in South

Florida, without cracking, blistering, splitting or pealing.